




**BUREAU
VERITAS**

MODINT TEST REPORT

Technical Report: (9325)310-1108

Page 1 of 4
November 13, 2025



Report Number
(9325)310-1108

Bureau Veritas Consumer Products Services
(Guangzhou) Co., Ltd
No. 183, Shinan Road, Meilin Plaza, Dongcheng,
Nansha, Guangzhou, Guangdong Province, China
511453
Tel: (86) 20 2290 2088 Fax: (86) 20 3490 9303
Email: BVCPS_pyinfo@cn.bureauveritas.com
Website: cps.bureauveritas.com

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions>, and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. Statements of conformity are based on simple acceptance criteria without taking measurement uncertainty into account, unless otherwise requested in writing. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty, provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



**BUREAU
VERITAS**

MODINT TEST REPORT

**TO : GUSTAV MULLER KG
RUDOLF-DIESEL-STRASSE 27
TUTTLINGEN, 78532,
GERMANY**

LAB NO.: (9325)310-1108
FORM NO.: /
DATE IN: Nov 06, 2025
DATE OUT: Nov 13, 2025
NO. OF WORKING DAYS: /
PAGE 2 OF 4

ATTN : ANDREAS KAUFMANN

<u>OVERALL RATING</u>	
PASS	_____
FAIL	_____
DATA	_____X_____

Vendor:	GUSTAV MULLER GMGH & CO. KG	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	GUSTAV MULLER GMGH & CO. KG
P.O. No.:	/	Style No.:	427818: 1288+1725+1741
Sample Description:	HAT SAMPLE	Style Description:	/
Color:	BEIGE	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	/
SKU:	/	Age Group:	/

Product Category	HAT
Test Requested	SEE TEST PROPERTY
Previous Report No.	/

Submitted Fiber Content	/
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/



BUREAU
VERITAS

LAB NO: (9325)310-1108

Page 3 of 4

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
UV PROTECTIVE PROPERTIES IN TEXTILE FABRICS			X	SEE RESULT

TECHNICAL QUESTIONS (86)20-22902088
bvcps_pyinfo@cn.bureauveritas.com

GENERAL INFORMATION (86)20-22902088
bvcps_pyinfo@cn.bureauveritas.com

SIGNATURES Bureau Veritas Consumer Products Services
(Guangzhou) Co., Ltd

Quan Peng
Operation Manager



**BUREAU
VERITAS**

LAB NO: (9325)310-1108

Page 4 of 4

TEST PROPERTY

TEST RESULTS

REQUIREMENTS

UV PROTECTIVE PROPERTIES IN TEXTILE FABRICS (AS/ NZS 4399)

Method : AS/ NZS 4399

Test Item(s) : A Apricot/ dark blue body with white lining

Parameter	CAS No.	Unit	MDL	Result	Limit
				A	
Mean UPF	-	-	-	1985.07	-
Standard Deviation	-	-	-	28.80	-
Standard error	-	-	-	35.62	-
UPF Rating	-	-	-	50+	-
Protection Classification	-	-	-	Excellent	-
Mean UVA(315-400nm) Transmission	-	%	-	0.06	-
Mean UVB (290-315nm) Transmission	-	%	-	0.05	-
Conclusion	-	-	-	Data	-

Remarks:

1 Refer To AS 4399, the UPF classification system is :

Classification UPF Ratings

Minimum 15

Good 30

Excellent 50, 50+

2. The results given apply only to the colour and weight of fabric tested. Unless otherwise stated the fabric is tested dry and relaxed.

3. This UPF Rating is for the fabric and does not address the amount of protection which is afforded by the design of the article. The manipulations involved in garment manufacture such as stretching and sewing may lower the UPF of the material.

4. The protection offered by this fabric may be lessened :

i) At points where the fabric is in close contact with the skin such as across the shoulders

ii) If the fabric is stretched

iii) If the fabric is wet; and

iv) With time due to effects of normal wear.

C/N